



Chamäleon GmbH  
Rudolf-Diesel-Straße, 8a  
69115 Heidelberg-Germany  
Tel.: +49-(0)-6221 520440  
Fax: +49-(0)-6221 520449  
E-mail: [info@chamaeleon/produktion.de](mailto:info@chamaeleon/produktion.de)  
<http://www.chamaeleon/produktion.de>

## *TECHNICAL DATA SHEET*

### CHAMÄLEON GRAVEX PREMIUM

<b>Article number:</b>	<b>37215; 37225, 37235</b>
<b>Intended use:</b>	Car refinishing Product /Surface protection
<b>General characteristics:</b>	<p>Chamaeleon Gravex Premium is an underbodycoating based on synthetic resins and rubbers. This coating is quickly-drying and especially developed for a long-term gravel protection of front and rear aprons, sills, wheel arches, etc..</p> <p>This product is very tixotropic and can be applied drip-free. Furthermore, this product has a good stitch and can be painted over with any kind of lacquer system when the film is completely hardened. Drying can take place in the air and also in the oven. After application the result will be a closed, elastic and structured film with excellent rust- and gravel protection.</p> <p>Reduces the noise inside cars because of the sound-damping property.</p>

#### **Technical characteristics:**

<b>Colour:</b>	White/Grey/Black	
<b>Viscosity (20°C):</b>	9000±1500 cP	Brookfield sp.4, 6 rpm
<b>Solids:</b>	44-47%	DIN 53216
<b>Density (20°C):</b>	1.04±0.02 kg/L	DIN 51757
<b>Over paintable:</b>	After completely harden	
<b>Saltspraytest:</b>	1000 hours	DIN 50021

#### **Application:**

Surface must be clean, rust-free and dry.  
Shake the can well before use.  
For painting with synthetic paint, allow surface to harden. For painting with 2-component and nitropaint, allow surface to completely harden. Thinly apply 2-component and nitropaints and reapply after sufficient drying time.



Chamäleon GmbH  
Rudolf-Diesel-Straße, 8a  
69115 Heidelberg-Germany  
Tel.: +49-(0)-6221 520440  
Fax: +49-(0)-6221 520449  
E-mail: [info@chamaeleon/produktion.de](mailto:info@chamaeleon/produktion.de)  
<http://www.chamaeleon/produktion.de>

<b>Important:</b>	Do not spray on the exhaust or brake systems, as well as motor or movable parts. After use, thoroughly rinse the pistol with solvent. Do not block the air valve at the base of the pistol. Clogged pistol can cause can to explode.
<b>Application pressure:</b>	5-7 bar.
<b>Recommended thickness:</b>	approximately 1 mm at application.
<b>Removement:</b>	can be removed with solvents as White Spirit, boilingpoint nafta, xylene, toluene, etc.
<b>Packaging:</b>	in 1 litre cans in the colours white, grey and black. For airless applications.
<b>Standard Packaging:</b>	12 x 1 litre cans

*For the additional information that is not included to the Technical Data Sheet apply to the supplier: e-mail: [info@chamaeleon-produktion.de](mailto:info@chamaeleon-produktion.de)  
See information on safety in Safety Data Sheet.*